

Technical Data Sheet

Moplen EP548S

Polypropylene, Impact Copolymer



Product Description

Moplen EP548S is a nucleated heterophasic copolymer with antistatic agent used injection moulding applications.

It combines a good impact/stiffness balance with a high fluidity.

Moplen EP548S is typically used by customers in opaque containers, housewares, toys and in thin-walled containers for food packaging (e.g. margarine tubs, yoghurt pots, etc.).

Regulatory Status

For regulatory compliance information, see Moplen EP548S [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Europe
Application	Housewares; Opaque Containers; Sports, Leisure & Toys
Market	Consumer Products; Rigid Packaging
Processing Method	Injection Molding
Attribute	Contains Antistat; High Flow; Impact Copolymer; Nucleated

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	44	g/10 min	ISO 1133-1
Density	0.90	g/cm ³	ISO 1183-1
Mechanical			
Tensile Modulus	1550	MPa	ISO 527-1, -2
Tensile Stress at Yield	28	MPa	ISO 527-1, -2
Tensile Strain at Break	30	%	ISO 527-1, -2
Tensile Strain at Yield	5	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	5	kJ/m ²	ISO 179
(0 °C, Type 1, Edgewise, Notch A)	3.5	kJ/m ²	ISO 179
(-20 °C, Type 1, Edgewise, Notch A)	3	kJ/m ²	ISO 179
Ductile/Brittle Transition Temperature	-53	°C	ISO 6603-2
Thermal			
Vicat Softening Temperature, (A/50 N)	151	°C	ISO 306
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	95	°C	ISO 75B-1, -2

Notes

These are typical property values not to be construed as specification limits.



Mob : + 91 8910506413 / 9831235030

<https://www.interchemindia.in>